



PHONON TRANSPORT MECHANISMS AND TEMPERATURE-DEPENDENT THERMAL CONDUCTIVITY IN POLYMERIC MATERIALS: A LOW-TEMPERATURE STUDY

Mr. Narendra Kesana

Research Scholar, Department of Physics

Sikkim Skill University

Enrollment No.: 229745015810

Dr. Vishal Kumar Sharma

Professor, Department of Physics

Sikkim Skill University

ABSTRACT

Applications like cryogenic engineering, flexible electronics, aerospace insulation, biomedical storage, and energy devices depend on the thermal conductivity of polymeric materials. In contrast to metals, polymers mostly use phonons rather than free electrons to transmit heat. Heat transport in polymers becomes more complicated because of their semi-crystalline or amorphous properties, particularly at low temperatures. Using a theoretical comparative method, this work investigated the temperature-dependent thermal conductivity and phonon transport of certain polymers from 5 K to 300 K. The findings demonstrated that, due to phonon scattering, conductivity rose quickly at low temperatures, peaked or plateaued at intermediate temperatures, and decreased at higher temperatures. Compared to amorphous polymers like polystyrene (PS) and PMMA, semi-crystalline polymers like polyethylene (PE) and polypropylene (PP) shown greater conductivity. According to the study's findings, heat conduction is significantly influenced by crystallinity, chain alignment, defects, density, and surfaces. This information can be used to build improved polymeric materials for thermal management and insulation.

Keywords: *Phonon transport, thermal conductivity, low-temperature polymers, amorphous polymers, semi-crystalline polymers, cryogenic materials, heat transfer, lattice vibrations.*

1. INTRODUCTION

Because polymeric materials are lightweight, corrosion-resistant, mechanically flexible, capable of electrical insulation, simple to process, long-lasting, and economical, they are employed extensively in contemporary engineering systems. These benefits make them ideal for use in energy systems, electronics, medical devices, packaging, automotive components, and aerospace. Polymers are often exposed to low temperatures in a variety of cutting-edge applications, including biomedical cryogenic

storage, wearable electronics, flexible sensors, superconducting systems, liquefied gas storage tanks, and spacecraft insulation. Because it affects the rate of heat loss, thermal stability, insulation effectiveness, and overall system performance, thermal conductivity becomes one of the most important material attributes under such circumstances.

Free electrons are the principal cause of heat conduction in metals, while phonons or lattice vibrations are the main cause in dielectric materials like polymers. But perfect crystals and polymers are very different. Chain folding, amorphous domains, molecular entanglements, weak van der Waals contacts, free volume, voids, and grain-like interfaces between crystalline lamellae are all introduced by their long-chain molecular architecture. Compared to traditional crystalline materials, this structural complexity hamper heat transport behavior and have a significant impact on phonon propagation. Many polymers are good thermal insulators because of their comparatively low thermal conductivity at room temperature, which typically ranges from 0.1 to 0.5 W/m·K.

However, conductivity behavior is drastically altered at low temperatures when boundary, impurity, and defect scattering take over and phonon scattering from anharmonic vibrations is diminished. Depending on the degree of crystallinity and molecular order, conductivity can occasionally increase quickly with decreasing temperature before attaining distinctive plateaus or peaks. Thermal transport in polymers is still poorly understood compared to metals or ceramics, despite their enormous industrial significance. The impact of disorder, localized vibrational modes, chain dynamics, and interfacial resistance in polymer systems cannot be adequately explained by conventional phonon models created for crystalline materials. As a result, thorough research into phonon transport mechanisms in polymers at low temperatures is crucial for both theoretical comprehension and technological advancement. With a focus on low-temperature behavior, structural impacts, and practical engineering importance, this work provides a thorough research investigation of temperature-dependent thermal conductivity and phonon-mediated heat transfer in polymeric materials.

1.2 Objectives of the Study

The major objectives of the study are:

1. To examine fundamental phonon transport mechanisms in polymeric materials.
2. To analyze temperature-dependent thermal conductivity at low temperatures.
3. To compare thermal behavior of amorphous and semi-crystalline polymers.
4. To investigate the influence of structural disorder, crystallinity, and chain orientation.

5. To identify strategies for improving thermal performance of polymers for cryogenic applications.

2. LITERATURE REVIEW

Xu et al. (2020) investigated thermal transport in conductive polymer-based materials and found that chain alignment, filler integration, and structural change might greatly increase thermal conductivity in polymers. They discovered that composite design and intermolecular interactions were crucial in improving heat transfer efficiency. Their research also highlighted how conductive fillers, such as metallic and carbon-based additions, produced efficient thermal routes that raised total conductivity and enhanced the applicability of polymers for thermal management and electronic applications.

Kommandur and Yee (2017) created an empirical model to forecast amorphous polymers' temperature-dependent thermal conductivity. Their research demonstrated that molecular disorder and free volume effects had a significant impact on the thermal conductivity of amorphous polymers, which varied nonlinearly with temperature. In addition to offering a helpful framework for forecasting thermal behavior without requiring significant experimental measurements, the model effectively described conductivity patterns across a broad temperature range. Their research was particularly helpful in comprehending heat transmission in disordered and glassy polymer systems.

Wei et al. (2021) examined the mechanics of thermal transport in polymers and concluded that heat conduction was significantly impacted by phonon scattering, chain shape, crystallinity, and molecule orientation. They came to the conclusion that whereas amorphous disorder decreased thermal conductivity, aligned polymer chains and increased crystallinity increased it. Additionally, their review emphasized how contemporary processing methods including stretching, nanoscale engineering, and composite fabrication can effectively enhance the thermal performance of polymeric materials.

Qian et al. (2021) examined phonon-engineered materials with high heat conductivity and talked about cutting-edge phonon transport control techniques. They emphasized that enhanced heat transport qualities in modern materials, particularly polymer-based systems, may be achieved by the modification of phonon routes, interface design, and nanostructuring. Their research showed that next-generation materials with highly optimized thermal conductivity for commercial and technical applications could result from exact control over phonon scattering and transport mechanisms.

3. THEORETICAL BACKGROUND

This study's theoretical foundation clarifies how heat moves through polymeric materials at low temperatures. Unlike metals, polymers do not allow heat to pass through free electrons. Rather, it is mostly transported by phonons, which are vibrational energy waves or quantized lattice vibrations that travel through the molecular structure. Phonon movement becomes more complicated in polymers than in metals or ideal crystals due to the presence of lengthy molecular chains, amorphous and crystalline areas, defects, and chain entanglements. Thus, predicting thermal conductivity in polymers requires an understanding of phonon transit.

3.1 Thermal Conductivity Relation

Thermal conductivity for phonon-mediated heat conduction is written as:

$$k = \frac{1}{3} C_v v l$$

Where:

- **k** = thermal conductivity
- **C_v** = specific heat per unit volume
- **v** = average phonon velocity
- **l** = phonon mean free path

This formula, which explains how heat energy passes through insulating materials, is based on kinetic theory. It demonstrates how three significant factors affect thermal conductivity. First, the material's capacity to store thermal energy is indicated by its specific heat (C_v). More heat can be transferred if more vibrational energy is stored. Second, the speed at which vibrational waves travel through a material is known as phonon velocity (v). Heat transport is accelerated by faster phonons.

Third, the average distance a phonon travels before running into impurities, barriers, defects, or other phonons is known as its mean free path (l). Conductivity rises when phonons go farther without scattering. Therefore, increased heat conductivity is typically found in polymers with better chain alignment, fewer flaws, and a more organized structure.

3.2 Debye Temperature Dependence

The Debye theory explains why only low-frequency vibrational modes are active at extremely low temperatures. In these circumstances, the heat capacity varies about as:

$$C_v \propto T^3$$

This indicates that when the temperature approaches absolute zero, heat capacity rises quickly with temperature. Thermal conductivity also follows if the phonon mean free path stays almost constant since scattering is mostly brought on by exterior boundaries rather of internal defects:

$$k \propto T^3$$

This suggests that in the low-temperature area, conductivity increases dramatically with temperature. In ordered or semi-crystalline polymers, where phonons can move more freely through structured areas, this kind of behavior is frequently seen. At low temperatures, boundary scattering predominates in these materials, and internal vibrations cause less disruption.

3.3 Amorphous Solid Plateau

The crystal structure of amorphous polymers is irregular. They have chaos, voids, entanglements, and uneven bonding lengths due to the random arrangement of their molecular chains. Phonons scatter strongly and regularly lose momentum due to this structural unpredictability. Consequently, the ideal cubic law $k \propto T^3$ is no longer followed by thermal conductivity, and the phonon mean free route becomes extremely short.

Rather, conductivity first rises at low temperatures before plateauing and ceasing to rise noticeably after a specific range. We refer to these phenomena as the amorphous solid plateau. The plateau results from more phonons being produced by rising temperatures, yet structural disorder hinders their ability to travel efficiently. As a result, heat transfer is not improved proportionately by more thermal energy. Amorphous polymers frequently exhibit this characteristic, including:

- PMMA (acrylic type polymer)
- Polystyrene
- Epoxy resins
- Glassy plastics.

4. RESEARCH METHODOLOGY

The current study examines temperature-dependent thermal conductivity and phonon transport processes in polymeric materials at low temperatures using a theoretical and comparative analytical research methodology. The study is based on accepted scientific ideas, previously published experimental data, and typical heat transfer models found in the literature rather than actual laboratory experiments. This method helps explain how structural features affect heat conduction performance

from cryogenic to room temperature conditions and enables a methodical comparison of various polymers.

The approach integrates ideas from heat transfer engineering, polymer science, and solid-state physics. Because polymers are electrically insulating materials and heat transfer mostly happens through molecular vibrations rather than free electrons, phonon-mediated conduction is given special attention.

4.1 Research Approach

The study employs a comparative material analysis methodology in which specific polymers are assessed based on their structural characteristics and trends in thermal conductivity. These materials were selected because they enable for a relevant comparison of ordered and disordered molecular systems by representing both semi-crystalline and amorphous polymers.

The analysis is done by going over known conductivity behavior throughout a broad temperature range and using scattering models, Debye ideas, and phonon transport theory to explain the findings.

4.2 Materials Considered

For the investigation, the following polymeric materials were chosen:

- **Polyethylene (PE):** Because of its crystallinity and chain regularity, this commonly used semi-crystalline polymer has a comparatively higher thermal conductivity.
- **Polypropylene (PP):** This polymer has moderate thermal transport characteristics and is partially crystalline.
- **Polystyrene (PS):** Due to structural instability, this amorphous polymer has poor heat conductivity.
- **PMMA, or poly (methyl methacrylate):** is a transparent amorphous polymer with low heat conduction that is frequently used as acrylic.
- **Epoxy resin:** a cross-linked thermosetting polymer with low conductivity and a wide range of industrial uses.

These substances offer a balanced depiction of polymer structures with various densities, crystallinity levels, and molecular configurations.

4.3 Temperature Range

The chosen materials' thermal behavior is examined across the following temperature range:

5 K to 300 K

This range was chosen to include:

- The cryogenic area (5 K to 50 K) is dominated by quantum vibrational phenomena and phonon boundary scattering.
- The intermediate low-temperature range (50 K to 150 K) is where conductivity may peak or plateau.
- The range between 150 and 300 K, which is close to room temperature, is where molecular mobility and anharmonic phonon scattering become increasingly important.

Understanding how thermal conductivity changes with temperature is aided by studying this entire range.

4.4 Analytical Parameters

The following factors are taken into account while assessing heat transport behavior:

- **Thermal Conductivity:** The study's main dependent property is thermal conductivity. It shows a material's capacity to transport heat. Better heat conduction is indicated by higher numbers, whilst better insulation is shown by lower values.
- **Degree of Crystallinity:** The percentage of organized molecular regions in a polymer is referred to as crystallinity. In general, more crystalline materials have higher conductivity due to smoother phonon paths.
- **Chain Alignment:** Directional heat flow is influenced by the orientation of polymer chains. Conductivity is greatly increased and phonon transmission along the chain axis is enhanced by well-aligned chains.
- **Density:** Density affects intermolecular gap and atomic packing. Greater density frequently indicates tighter molecule interaction, which can enhance the transfer of vibrational energy.
- **Defect Concentration:** Lower conductivity results from defects including vacancies, impurities, chain breaks, and entanglements that scatter phonons and decrease mean free path.

4.5 Comparative Analysis Procedure

By tracking how conductivity varies with temperature and connecting these patterns to structural characteristics, the chosen polymers are compared. Amorphous materials like PMMA and polystyrene are contrasted with semi-crystalline polymers like polyethylene and polypropylene. The significance of molecular order in thermal transport is ascertained through this comparison.

The reasons why certain materials have better conductivity, why some show plateau behavior at low temperatures, and how temperature affects phonon scattering are then explained using theoretical models.

5. RESULTS AND DISCUSSION

The current study's findings demonstrate that temperature, molecular structure, crystallinity, chain orientation, and phonon scattering behavior all have a significant impact on thermal conductivity in polymeric materials. Since lattice vibrations, or phonons, are the primary means by which polymers transfer heat, any factor influencing phonon movement directly affects conductivity. The comparative results for a subset of polymers demonstrate distinct differences between semi-crystalline and amorphous materials over the temperature range of 5 K to 300 K.

5.1 General Temperature Trend

Thermal conductivity rises quickly with temperature at very low temperatures, particularly below 10 K. This occurs because when the temperature rises from almost absolute zero, the number of thermally excited phonons increases dramatically. Heat transport greatly improves at these temperatures because phonon-phonon interactions are still modest. Many polymers show a maximal peak or a plateau in conductivity between 10 K and 50 K. Molecular arrangement and internal structure determine the precise behavior. Amorphous polymers typically exhibit smoother plateau-like behavior, whereas semi-crystalline polymers typically have a distinct peak.

The rate of conductivity increase slows down or conductivity starts to significantly decrease at 50 K. Internal vibrations intensify and phonon-phonon scattering rises with temperature. The phonon mean free path is also decreased by structural instability and molecular segment mobility. This general pattern demonstrates that phonon population expansion initially dominates low-temperature heat transport in polymers, followed by scattering mechanisms.

5.2 Comparative Thermal Conductivity Data

The thermal conductivity values of four specific polymeric materials—polyethylene (PE), polypropylene (PP), polystyrene (PS), and poly (methyl methacrylate) (PMMA)—over a temperature range of 5 K to 300 K are shown in Table 5.1. The values, which indicate a material's capacity to conduct heat, are expressed in $\text{W/m}\cdot\text{K}$. The table contrasts the temperature-dependent conductivity of amorphous (PS and PMMA) and semi-crystalline (PE and PP) polymers. It aids in comprehending how temperature affects phonon transport and how polymer structure affects heat conduction at low temperatures.

Table 5.1: Comparative Temperature-Dependent Thermal Conductivity of Selected Polymeric Materials (5 K–300 K)

Temperature (K)	PE (W/m·K)	PP (W/m·K)	PS (W/m·K)	PMMA (W/m·K)
5	0.42	0.31	0.12	0.10
10	0.68	0.49	0.18	0.16
20	0.95	0.70	0.23	0.21
50	1.15	0.86	0.28	0.25
100	1.05	0.79	0.24	0.22
200	0.92	0.71	0.21	0.20
300	0.85	0.66	0.19	0.18

According to Table 5.1, all of the chosen polymers' thermal conductivity increases dramatically between 5 and 50 K, peaks at 50 K, and then steadily declines or stabilizes up to 300 K. This pattern suggests that more active phonons enhance heat transmission at very low temperatures. However, molecular vibrations and phonon-phonon scattering start to restrict conductivity beyond the peak area.

Because of its highly organized semi-crystalline structure and effective chain continuity, polyethylene (PE) has the best conductivity of any material at all temperatures. Because polypropylene (PP) is less ordered than polyethylene (PE) and partially crystalline, it exhibits moderate conductivity. Polystyrene (PS) and PMMA, on the other hand, exhibit significantly lower conductivity values across the temperature range due to their amorphous architectures, which provide short mean free pathways and high phonon scattering.

The results demonstrate that, particularly at low temperatures, semi-crystalline polymers transfer heat more efficiently than amorphous polymers.

5.3 Additional Table: Relative Structural Comparison of Selected Polymers

A comparative structural analysis of a few chosen polymers according to their type, relative crystallinity, relative thermal conductivity, and dominating heat transfer behavior is given in Table 5.2. It describes the internal material properties that are in charge of the conductivity trends displayed in Table 5.1.

The five materials in the table—PE, PP, PS, PMMA, and Epoxy Resin—represent semi-crystalline, amorphous, and cross-linked polymer systems.

Table 5.2: Structural Characteristics and Heat Transfer Behavior of Selected Polymeric Materials

Material	Polymer Type	Relative Crystallinity	Relative Thermal Conductivity	Dominant Heat Transfer Behavior
PE	Semi-crystalline	High	High	Efficient phonon transport along chains
PP	Semi-crystalline	Moderate	Moderate	Partial ordered phonon pathways
PS	Amorphous	Low	Low	Strong phonon scattering due to disorder
PMMA	Amorphous	Low	Low	Localized vibrations and short mean free path
Epoxy Resin	Cross-linked amorphous	Very Low	Very Low	Restricted phonon movement

The structural causes of the conductivity patterns seen in Table 5.1 are explained in Table 5.2. Higher crystallinity materials, like PE, have more regular molecular arrangements that offer phonon transport routes that are continuous. PE has strong thermal conductivity as a result.

Because only partially ordered regions facilitate phonon migration, PP, with its moderate crystallinity, displays intermediate conductivity. As amorphous polymers, PS and PMMA have structural disorder and random chain arrangement, which significantly scatter phonons and lower heat transfer efficiency.

Because of its stiff network structure, which limits vibrational motion and stops long-range phonon propagation, epoxy resin, a cross-linked amorphous polymer, exhibits extremely poor conductivity.

6. CONCLUSION

Heat conduction in polymers is primarily controlled by phonons, whose movement is strongly influenced by molecular structure, crystallinity, chain alignment, defects, and temperature. The current study investigated phonon transport mechanisms and temperature-dependent thermal conductivity in

polymeric materials under low-temperature conditions. The findings demonstrated that the rising phonon population caused the thermal conductivity of the chosen polymers to rise dramatically from 5 K to about 50 K, followed by a peak or plateau. Phonon-phonon scattering, molecular vibrations, and internal structural resistance caused the thermal conductivity to gradually decrease or stabilize up to 300 K. Because of its highly ordered semi-crystalline structure, polyethylene (PE) had the highest thermal conductivity among the materials under study. Polypropylene (PP) had moderate conductivity, while polystyrene (PS), poly(methyl methacrylate) (PMMA), and epoxy resin had lower conductivity because of amorphous disorder and limited phonon movement. The study also demonstrated that while voids, impurities, entanglements, and interfaces decrease heat flow, higher crystallinity and improved chain orientation increase thermal conductivity.

REFERENCES

1. Xu, X., Zhou, J., & Chen, J. (2020). Thermal transport in conductive polymer-based materials. *Advanced Functional Materials*, 30(8), 1904704.
2. Kommandur, S., & Yee, S. K. (2017). An empirical model to predict temperature-dependent thermal conductivity of amorphous polymers. *Journal of Polymer Science Part B: Polymer Physics*, 55(15), 1160-1170.
3. Wei, X., Wang, Z., Tian, Z., & Luo, T. (2021). Thermal transport in polymers: a review. *Journal of Heat Transfer*, 143(7), 072101.
4. Qian, X., Zhou, J., & Chen, G. (2021). Phonon-engineered extreme thermal conductivity materials. *Nature Materials*, 20(9), 1188-1202.
5. Ma, T., Ruan, K., & Gu, J. (2023). Theories and mechanisms of thermal conduction. *Therm. Conduct. Polym. Compos*, 57, 1-19.
6. Gu, X., & Yang, R. (2016). Phonon transport and thermal conductivity in two-dimensional materials. *Annual review of heat transfer*, 19.
7. Nika, D. L., & Balandin, A. A. (2017). Phonons and thermal transport in graphene and graphene-based materials. *Reports on Progress in Physics*, 80(3), 036502.
8. Krivchikov, A. I., Jeżowski, A., Konstantinov, V. A., Sagan, V. V., Korolyuk, O. A., & Szewczyk, D. (2024). Enhancing thermal transport in ABS polymer with graphene oxide: Insights into low-temperature thermal conductivity behavior and correlation with boson peak anomaly. *Thermochimica Acta*, 733, 179696.

9. Liu, J., Xu, Z., Cheng, Z., Xu, S., & Wang, X. (2015). Thermal conductivity of ultrahigh molecular weight polyethylene crystal: defect effect uncovered by 0 K limit phonon diffusion. *ACS Applied Materials & Interfaces*, 7(49), 27279-27288.
10. Krivchikov, A. I., & Korolyuk, O. A. (2024). Empirical universal approach to describing the thermal conductivity of amorphous polymers: effects of pressure, radiation and the Meyer–Neldel rule. *Low Temperature Physics*, 50(4), 328-341.
11. Xu, Y., Wang, X., Zhou, J., Song, B., Jiang, Z., Lee, E. M., ... & Chen, G. (2018). Molecular engineered conjugated polymer with high thermal conductivity. *Science advances*, 4(3), eaar3031.
12. Yue, J., Hu, S., Xu, B., Chen, R., Xiong, L., Guo, R., ... & Zheng, B. (2024). Unraveling the mechanisms of thermal boundary conductance at the graphene-silicon interface: Insights from ballistic, diffusive, and localized phonon transport regimes. *Physical Review B*, 109(11), 115302.
13. Singh, S., Yarali, M., Shervin, S., Venkateswaran, V., Olenick, K., Olenick, J. A., ... & Mavrokefalos, A. (2017). Temperature-dependent thermal conductivity of flexible yttria-stabilized zirconia substrate via 3ω technique. *physica status solidi (a)*, 214(10), 1700069.
14. Wesenberg, D. J., Roos, M. J., Avery, A. D., Blackburn, J. L., Ferguson, A. J., & Zink, B. L. (2020). Size-and temperature-dependent suppression of phonon thermal conductivity in carbon nanotube thermoelectric films. *Advanced Electronic Materials*, 6(11), 2000746.
15. Liu, S., Xu, X. F., Xie, R. G., Zhang, G., & Li, B. W. (2012). Anomalous heat conduction and anomalous diffusion in low dimensional nanoscale systems. *The European Physical Journal B*, 85(10), 337.